

112.2 - Cemented Carbides (powder form)

SRMs 887-889 are prepared from sintered tungsten carbide base materials.

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	Description	Unit of Issue	Cobalt	Tantalum	Titanium	Carbon
887	Cemented Carbide (W-83,Co-10)	100 g	10.35			(5.5)
888	Cemented Carbide (W-64,Co-25,Ta-5)	100 g	24.7	4.77		(4.6)
889	Cemented Carbide (W-75,Co-9,Ta-5,Ti-4)	100 g	9.50	4.60	4.03	(6.0)

Values in parentheses are not certified and are given for information only.